


FUTURA Md Bt FONT 0.060" HEIGHT
CENTERED IN POCKET, FLUSH
TO SURFACE

TOP FINISH - SPI-B2
NO TOOL OR SCUFF MARKS



SCALE 1:1

Tensile Strength	ASTMD412	Mpa	9.2
Elongation at break	ASTMD412	%	194.8
Hardness	ASTMD2240		89
Compression set (70hrs @ 100°C)	ASTMD395	%	6.6
Density	ASTMD3165		1.24
Heat aging (70hrs @ 125°C)			
Change in Tensile strength	ASTMD573	%	-19.6
Change in Elongation	ASTMD573	%	-59.5
Change in Hardness	ASTMD573		7
Compression Stress Modulus			
Compression 5%		Mpa	1.35
Compression 10%		Mpa	2.36
Compression 20%		Mpa	5.16
Compression 25%		Mpa	5.89

NOTES:

PEROXIDE CURED, RoHS APPROVED

This drawing, design, and/or concept, along with all of the contents herein are the exclusive ownership of Vicone High Performance Rubber Inc. Its reproduction and/or distribution are strictly prohibited. Copyright Vicone High Performance Rubber Inc.

TOLERANCES - IMPERIAL
(unless specified otherwise)

RMA-A3-T0.016"



Drawn
John Fisher

Date
05/10/11

Checked
Eric Leclair

Date
07/07/11

Approved
Eric Leclair

Date
03/09/12

Material
VicoSil™909E - 90 DURO

Colour
BLACK

Finish
SEE NOTES



VICONE High Performance Rubber Inc.
12-216 Poirier Street
St. Eustache, Quebec, J7R 6B1
www.viconerubber.com
877-VICONE2 (842-6632)

Title -
HEX SAMPLE #6

Scale:2:1

Sheet 1 of 1

DWG #
MD00417

Rev #
00