


SCALE 1:1

TOP FINISH - SPI-B2
NO TOOL OR SCUFF MARKS



Tensile Strength	ASTMD412	Mpa	6.4
Elongation at break	ASTMD412	%	900
Hardness	ASTMD2240		20
Compression set (22hrs @ 302°F)	ASTMD395	%	6.36
Density	ASTMD3165		1.23
Heat aging (70hrs @ 200°C)			
Change in Tensile strength	ASTMD573	%	9.9
Change in Elongation	ASTMD573	%	-24
Change in Hardness	ASTMD573		-27.5
Compression Stress Modulus			
Compression 5%		Mpa	0.39
Compression 10%		Mpa	0.62
Compression 20%		Mpa	1.31
Compression 25%		Mpa	2.02

NOTES:

PLATINUM CURED, USP CLASS VI, RoHS APPROVED

This drawing, design, and/or concept, along with all of the contents herein are the exclusive ownership of Vicone High Performance Rubber Inc. Its reproduction and/or distribution are strictly prohibited. Copyright Vicone High Performance Rubber Inc.

TOLERANCES - IMPERIAL
(unless specified otherwise)

RMA-A2-T0.016"



Drawn John Fisher	Date 05/10/11
Checked Eric Leclair	Date 07/07/11
Approved Eric Leclair	Date 03/09/12
Material VicoSil™0591EK - 20 DURO	
Colour CRYSTAL CLEAR	
Finish SEE NOTES	



VICONE High Performance Rubber Inc.
12-216 Pointier Street
St. Eustache, Quebec, J7R 6B1
www.viconerubber.com
877-VICONE2 (842-6632)

Title -
HEX SAMPLE #1

Scale:2:1

Sheet 1 of 1

DWG #
MD00411

Rev #
00